

## TECHNICAL DOCUMENTATION

### Grabber Acoustical Sound and Smoke Sealant (GSCSF)



#### Physical Properties:

Type:	Siliconized elastomeric acrylic	VOC:	< 50 g/L
State:	Med.-viscosity mastic	Weight per gallon:	13 lb
Solids:	79%	Flashpoint:	> 200 °F
Viscosity:	170,000 cps	Freeze/Thaw Stability:	Stable
pH:	7.0	Storage Life:	24 mo. unopened, above 75 °F

#### Application Guidelines:

- Application Temperature: Above 40°F
- Service Temperature Range: -20°F to 150°F
- Working Time: Approximately 10-15 minutes for a 1/4 "bead
- Application Directions: 1) Surfaces must be clean and free of any material that may prevent adequate adhesion. 2) Cut tip to desired bead size. 3) Puncture inner seal and place in cartridge gun. 4) Apply sealant underneath all runners at the ceiling and floor. 5) Sealant should also be applied to all openings including cutouts, electrical boxes, perimeter joints, and other areas where sound transmission and air infiltration may occur. No tooling is required. It is the sole responsibility of the user to thoroughly test any proposed use with all substrates to determine project suitability.
- Cleanup: Clean uncured material with water. After curing, excess sealant must be cut or scraped away.

## TECHNICAL DOCUMENTATION

### Grabber Professional Drywall Adhesive (GDWAV)

---

#### Features & Benefits:

- Prevents smoke and flame spread
- Improves sound transmission (STC) ratings
- Cleans easily with water in wet state
- Mold and mildew resistant
- Paintable
- VOC-compliant

---

#### Limitations:

Not designed for continuous submersion or use below the waterline. Air, sealant, and surface temperature should be above 40°F. Do not apply if rain is expected within 12 hours.

---

#### Specifications:

- ASTM C834 Type OP Grade -18°C
- ASTM C920 Type S, Grade NS, Class 25, M, G, and A

---

#### Compatible Materials:

Common building materials including wood, metal, gypsum wallboard, masonry, stone, ceramic tile, concrete, marble, aluminum, and piping, including PVC and CPVC.

---

#### Important Notice:

Our recommendations, if any, for the use of this product are based on tests believed to be reliable. Since the use of this product is beyond the control of the manufacturer, no guarantee or warranty, expressed or implied, is made as to such use or effects incidental to such use, handling or possession or the results to be obtained, whether in accordance with the directions or claimed so to be. The manufacturer expressly disclaims responsibility therefore. Furthermore, nothing contained herein shall be construed as a recommendation to use any product in conflict with existing laws and/or patents covering any material or use.