

**Specification Sheet
#706**

Type: Hot Melt Glue - Ethylene Vinyl Acetate (PMHG2515)

Solids: 100%

Viscosity ¹: @ 250° (F) (cps) 25,000
@ 325° (F) (cps) 6,200
@ 375° (F) (cps) 3,000

Softening Point 176° F

Open Time: 45-65 seconds

Color: Tan

Odor: Slight

Shelf Life: Indefinite

Flash Point: Above 450° (F)

FDA Status: Compositional compliance with FDA Regulation #21CFR175.105 for food packaging.

Storage: Common Storage

Application Temperature: 350° (F) to 400° (F)

Suggested Uses: A hot melt adhesive designed for bonding gypsum board. Offering long open time and high delivery rate.

Shelf Life 12 Months

Precautions: Do Not Mix with other adhesives
Severe burns will result if contact is made in molten state.
Material safety data sheets provide safety precautions that should be observed in handling and storing.

The buyer should conduct its own tests of this product before use to determine proper preparation technique and suitability for proposed application. FPC warrants that the product conforms with FPC written specifications, and is free from defects. FPC disclaims all other warranties, expressed or implied, including the warranties of merchantability and fitness for a particular purpose. The buyer's sole remedy for non compliance with this warranty shall be for the replacement of the product or refund of the buyer's purchase price.

¹ Brookfield Viscosity – ASTM D3236 using spindle SC4-27