



TECHNICAL PRODUCT BULLETIN Acrylitex Vapor Prime

Physical Characteristics

Weight per Gallon: 12 ± 3 lb	pH: 9 ± 1
% Solids by Weight: 45 ± 7%	Substrate: Gypsum wallboard, concrete
% Solids by Volume: 32 ± 7%	Pre-Treatment: None
Viscosity @ 78°F (25.5°C): 1400 ± 500 cps	Form: Liquid, Ready-to-Use
Flash Point (Closed Cup): None	Color: White
Spreading Rate: 459 ± 50 ft ² @ 1 dry mil	Odor: Mild Latex
Material VOC: < 50 g/ltr (0.15 lb/gal)	Carrier: Water-base
Coating VOC (minus water): < 85 g/ltr (0.8 lb/gal)	

Note: a certified product data sheet detailing VOC content will be available upon request from Acrylic Technologies, Inc. Environmental Department.

Application Specifications

Method: Product can be applied by spray application.

Drying Schedule: Ambient air, forced air **Reduction:** None

Special Notes

Effect on Freezing: DO NOT FREEZE; product will not recover

Shelf Life: 12 months - please rotate stock on a regular basis

Regulatory Status: This product is not considered a hazardous waste under current RCRA regulations. This product does not contain, nor is it manufactured using ozone-depleting substances as listed under Section 611 of the Clean Air Act.

Before using this product, please read the Material Safety Data Sheet for Acrylitex Vapor Prime and follow the recommended safety instructions.

WARRANTY – The information and recommendations contained on labels and in bulletins offered by this company are to the best of our knowledge, accurate and reliable. No guarantee of their accuracy is made, however, and the products discussed are sold upon condition that the purchaser shall make his own tests to determine the suitability of such products for his particular purposes and uses. Nothing in bulletins or on labels constitutes permission or a recommendation to practice or use any invention covered by any patent by any company or person. Our liability will be limited to replacement of merchandise found to be defective by company representatives. The manufacturer shall not be liable for any representations (express or implied) made by any